

**STRUCTURAL COMPONENT CONSISTING OF FIBRE-REINFORCED  
THERMOPLASTIC PLASTIC**

The invention concerns a structural component consisting of fibre-reinforced thermoplastic plastic in accordance with the generic term of claim 1 as well as a  
5 method for manufacturing such a structural component and an installation for implementing this method.

00673340-101400

Such known fibre-reinforced preformed - and structural components in general can be manufactured either with cost-effective series production methods and with only a relatively low fibre reinforcement, with which - while a broad variety of shapes is  
10 possible - load-bearing functions cannot be accomplished. Or else relatively expensive, elaborate methods with a high proportion of continuous fibre are called for, which enable structural components for demanding load-bearing functions, whereby the forming here, however, frequently is limited, resp., would once again require an increased expenditure. With the known cost-effective manufacturing  
15 methods, short- or long-fibre-reinforced preformed components can be produced with a relatively low proportion of fibre and correspondingly limited mechanical characteristics, such as strength, rigidity, brittleness and creep behaviour. Such methods are, e.g., short-fibre injection moulding, which makes possible a very good shaping, but which as a result of the very limited fibre lengths utilizable (usually less  
20 than 3 mm) and the comparatively low proportions of reinforcing fibres, however, are mechanically still relatively weak and brittle. In the case of a further known method, the long-fibre extrusion, greater fibre lengths of over 5 mm, e.g., 10 - 30 mm are possible, which with a good consolidation in part make possible improved mechanical characteristics, above all also reduced thermal expansions. Various methods for the  
25 suitable corresponding-to-form feeding in of the long-fibre molten mass are known, e.g., by means of conveyor belts and blades for separating the molten mass in the mould or by means of a controlled laying device in accordance with EP 769 358.

- With a corresponding-to-form feeding in, short flow paths and careful treatment of the long-fibres can be achieved. However, also with this no load-bearing structures are feasible. In particular demanding load-bearing structural components, such as, e.g., for vehicle cabins, chassis components or load-bearing body components or also for light, but stable transport containers, sports implements, etc., cannot be manufactured with this known method. In addition to the high mechanical requirements of load-bearing structural components in vehicle manufacture, apart from high strength values above all also a high creep resistance and a favourable crash characteristic with a defined adjustability and a high energy absorption are demanded.
- Such demanding load-bearing structural components are feasible with continuous fibre-reinforced composite components, however, they call for very elaborate, expensive manufacturing processes. These are, e.g., the squeeze moulding of plane thermoplastic continuous fibre semi-finished products (organo-sheet pressing), which, however only allows a limited shaping or else requires a once again increased effort for a more elaborate shaping. Also load-bearing structural components made of high-strength duomer composite materials can only be produced by elaborate and expensive processes, in general require relatively long cycle times and also with respect to re-cycling lead to additional problems. They are therefore not utilizable for larger series in vehicle production.
- It is therefore the object of the invention presented her to overcome these limitations, resp., disadvantages of the known methods and structural components and to create a load-bearing structural component as well as a corresponding manufacturing method and to indicate an installation for the manufacture of a structural component, which can reliably fulfil demanding load-bearing functions and which structural component can be manufactured cost-effectively and in different shapes, whereby also short cycle times for a series production can be achieved. Over and above, also additional functions, such as, e.g. the introduction of forces into the structural component shall be possible.

09673340-101400

This object is solved in accordance with the invention by a structural component in accordance with claim 1, a method in accordance with claim 21 and an installation for the implementation of the method in accordance with claim 35.

With the invention, in essence advantageous characteristics of long-fibre  
 5 compression-moulded components, which make possible a broad range of shapings, combined with the high mechanical characteristics, which form the integrated load-bearing supporting structure with at least one load-transmitting internal connecting area of the continuous fibre strands, in that in a simple manner in one manufacturing process relatively cost-effectively and with short cycle times light and load-bearing  
 10 structural - and preformed components can be made.

The dependent claims concern advantageous further developments of the invention, which for various applications make possible particular advantages with respect to producibility, mechanical characteristics, weight and manufacturing costs as well as additional functions.

15 In the following, the invention is further explained on the basis of embodiments and Figures. These show:

- Figs. 1a,b a structural component in accordance with the invention in cross-section through a continuous fibre strand and at an internal connecting area,
- 20 Figs. 2, 3 arrangements of continuous fibre strands as load-bearing structure in structural components,
- Figs. 4, 5 twisted and wrapped continuous fibre strands,
- Figs. 6a, b a load-bearing insert on a continuous fibre strand,

09673340-101400

- Fig. 7 a structural component with inlays,
- Figs. 8, 9 structural components with three-dimensional profile cross-sections,
- Fig. 10 an external connecting area,
- Fig. 11 a structural body formed out of several structural components,
- 5 Fig. 12 a structural body, formed out of two half-shells,
- Fig. 13 a transport mesh with laid continuous fibre strands,
- Fig. 14 a structural component with two layers of continuous fibre strands,
- Fig. 15 a vehicle side wall with framework-like supporting structure,
- Fig. 16 a continuous fibre strand with an eye moulded into it,
- 10 Fig. 17 a holding element at the end of a continuous fibre strand,
- Fig. 18 a movable fixing pin for the positioning of continuous fibre strands,
- Figs. 19a, b installations for the manufacturing of structural components,
- Figs. 20a, b shapings of the laying path in a form tool,
- Fig. 21 a thermal conditioning of a laying path,
- 15 Figs. 22a, b, c guiding - and pressing on means for the laying of continuous fibre strands,
- Figs. 23a, b a connecting layer as interface with a transition zone,
- Figs. 24a, b, c load-transmitting internal connecting areas of two continuous fibre strands,
- 20 Fig. 25 a supporting structure arrangement of continuous fibre strands with fixing - and tensioning elements.

The Figs. 1a, 1b, for example, illustrate the structure of a structural component made of fibre-reinforced thermoplastic plastic material. Fig. 1a illustrates a cross-section through a continuous fibre strand 3 and Fig. 1b shows a load-transmitting internal connecting area 7 of two continuous fibre strands. The structural component has a shaping long-fibre-reinforced thermoplastic matrix 2 and an integrated load-bearing supporting structure 4, which is formed by consolidated continuous fibre strands 3 with a thermoplastic matrix. Essential here is the fact, that the long-fibre matrix and the continuous fibre matrix are compatible with one another to such an extent, that

they are fused together at their mutual contact surfaces 6 (interface), i.e., that they are thermoplastically joined. The supporting structure 4 has at least one load-transmitting internal connecting area 7 between two continuous fibre strands 3. In order to achieve particularly good connections at the interfaces, the interfaces 6 can at least in part be implemented as connecting layers 6a, which form a transmission zone between the long-fibre matrix 2 and the continuous fibre strands 3. This is further explained in the Figs. 23a and 23b. Advantageously, the interfaces 6 for the purpose of an optimum connection and load-transmission from the continuous fibre strands to 3 the long-fibre mass 2 can also be designed as enlarged structured interfaces 6b manifesting structured uneven extrusions. This is also illustrated in the Figs. 4, 5.

Fig. 1b illustrates a force-transmitting internal connecting area 7 between two continuous fibre strands 3, which are of decisive significance for the mechanical stability of the supporting structure 4. For a good load transmission, to do so an optimum thermoplastic connection, in preference at relatively large interfaces F7, has to be produced. To achieve this, the strands 3 at the connecting area 7 are strongly flattened and widened. Further illustrations for this are shown in the Figs. 24a, b, c.

The continuous fibre strands 3, depending on requirements of the resulting structural component, can be utilized in various shapes, both with respect to cross-sectional shapes (round, flat, etc.), as well as with respect to their composition and surface structure. Thus, e.g., UD-fibres, prepregs, rovings and in complement fabric tapes, knitted or fibrous layers can be utilized.

Examples of this supporting structure 4 are shown in the Figs. 2 and 3, whereby the continuous fibre strands 3 in preference form at least one closed mesh 10 with a load-transmitting internal connection area 7. Fig. 2, as an example, illustrates a closed mesh or loop 10 as supporting structure and outer frame of a vehicle tailgate 95, the

shape of which is formed by the long-fibre matrix 2.

Fig. 3 shows a supporting structure 4, in the case of which the continuous fibre strands, running in different directions, form a framework-like pattern 11 and are thermoplastically connected at internal connection areas 7. The supporting structure 4 of a structural component in doing so can be composed of a single strand, or it is possible also to utilize several strands, if so required with differing thicknesses and cross-sectional shapes. It is important, that a material connection between the long-fibre matrix 2 and the continuous fibre strands 3 is achieved, for which reason the matrix materials of the two elements in preference are identical, at least, however, compatible to such an extent, that the two materials are mixed together by means of diffusion at the interface layers 6.

Suitable as matrix materials for the long-fibre reinforcement 2 and the continuous fibre strands 3 are polypropylene (PP), polyamide (PA), polyethyleneterephthalate (PET), polybutyleneterephthalate (PBT), thermoplastic polyurethanes (PUR), polycarbonate (PC) as more cost-effective technical plastic materials for corresponding applications, while polyimides (PI), polyphenylsulphide (PPS) or polyetheretherketone (PEEK) are conceivable for particularly demanding applications.

As reinforcing fibres 13 of the continuous fibre strands 3, in preference glass, for demanding applications also carbon or aramide are utilized, while for the long-fibre reinforcement 12 in most instances cost-effective glass fibres are sufficient.

With the continuous fibre strands of the supporting structure 4, the high mechanical properties of the structural components are achieved, while the long-fibre

reinforcement 2 provides a shaping - and supporting function. In this it is essential, that between the continuous fibre strands and the long-fibre reinforcement a very good contact and a good load transmission is achieved, for which the long-fibre reinforcement should also have a sufficiently high fibre content, in order with this to also minimize the differences in the thermal expansion. The reinforcement of the long-fibre matrix should therefore have a fibre content of at least 10 % by volume, in preference 15 to 25 % by volume. While the continuous fibre strands 3 have a fibre content of at least 40 % by volume, in preference of 45 to 60 % by volume.

In order to be in a position, dependent on the laying paths 39 (Fig. 13), to bend and also if so required to shape the continuous fibre strands, these are in preference twisted in accordance with Fig. 4. In order to hold them together well also during pressing, the continuous fibre strands 3 can also be wrapped (16 in Fig. 5) or enveloped by a braided tube 17. With this, also a structured, enlarged connecting layer 6a with shapings can be achieved. A further advantageous improvement of the contact can be obtained with needle-bonding 18, in the case of which fibre ends protrude from the strands 3 in all directions and therefore reach into the re-melted long-fibre mass 2. Fig. 4 illustrates a round -, Fig. 5 a flat cross section. The continuous fibre strands 3 have to a greater extent longitudinally oriented continuous fibres, which are fully impregnated with matrix material, compacted and consolidated. During the manufacture of the consolidated continuous fibre strands, the twisting can also be carried out with differing strengths, depending on whether during the laying on the laying path greater or smaller bends occur, i.e., a continuous fibre strand can in the zone of greater bending have a correspondingly stronger twisting and in zones with weaker bending a very low twisting. If no lateral bends occur, it is also possible to utilize flat strands without any twisting, i.e., in essence UD strands.

The long-fibre reinforcement produced by extrusion in preference has greater fibre lengths than is possible in the case of injection moulding. To achieve this, a great

proportion of the fibres should have a length of at least 5 mm, whereby preferably the fibre length to a great extent can lie within a range of 10 to 30 mm. Important is an impeccable impregnation, mixing and consolidation also of the long-fibre reinforcement.

- 5 Since the plastified continuous fibre strands 3 during laying can be moved and re-shaped in any direction, in a simple manner also load-bearing inserts 21, as depicted in Fig. 6, can be joined to the continuous fibre strands, resp., enveloped by them. With this, load-bearing elements, e.g., fixing elements, such as safety belt anchor points in vehicle cabins, can be manufactured (Fig. 15).
- 10 Fig. 6a in cross section and Fig. 6b from above show an example of a two-part insert 21, which by the closing of the mould is pressed together to the required position and as a result by means of a corresponding flank 19 can in addition also tension the continuous fibre strands 3 in a defined manner. In the insert, a screw thread 20 is attached. On the right side in Fig. 6a lies the overlap of the continuous fibre strand 3,
- 15 which here is correspondingly pressed together and deformed to a greater extent.

- Depending on the requirements of the structural component, apart from inserts also other inlays can be incorporated, as is illustrated in Fig. 7. Here, for example, a high-strength continuous fibre strand-reinforced tubular profile component 23 with a flattened end is connected to a continuous fibre strand 3, whereby here in addition a
- 20 local continuous fibre strand fabric inlay 24 supports the load introduction. Important is always the impeccable thermoplastic connection of the elements.

The wide-ranging design - and shaping possibilities of the structural components in accordance with the invention are illustrated in the Figs. 8 and 9, which form three-



dimensional „profile cross sections“ 26, 27. Fig 8 in doing so shows a slightly open U-profile composed of three continuous fibre strands 3.1 - 3.3, which is connected with the long-fibre mass 2 through a ribbing 28.

Fig. 9 illustrates, for example, a section through a frame girder 27 of a vehicle cabin, which contains a flange 29 for receiving a window pane and which in turn has strengthening ribs 28 in combination with the load-bearing profiled, flat continuous fibre strands 3.

Advantageously and depending on the application, open external connecting areas 8 can be formed on the structural components, which consist of continuous fibre strands, in order by means of this to assure the best possible load introduction into the structural component, as is illustrated in the example of Fig. 10 by corresponding form tool components 51.1, 51.2 (refer to Fig. 19). With this, structural bodies 90 can be assembled out of several individual structural components 1 to a great extent in any desired manner, in that these structural components are connected to one another at external connecting areas 8, which are preferably formed out of continuous fibre strands. This in preference can be accomplished by welding or if need by also by glueing. In analogy to the internal connecting areas 7, these external connecting areas 8 too are preferably designed with a large surface area.

The example of Fig. 11 shows a vehicle cabin, which is composed of a floor group 96, two side walls 97, a rear part 98 and a front part 99 by connecting the areas 8.

Fig. 12 illustrates a further example of a structural body, which is composed of two structural components 1, here designed as half shells: a U-profile 92 and a cover 93, which together form the hollow profile support 91 with differing cross-sectional

09673340-101400

shapes of the CF strands 3.

The following method is suitable for manufacturing structural components in accordance with the invention, which can, e.g., be carried out with an installation as illustrated in Fig. 19:

- 5 A plastified, long-fibre-reinforced plastic mass is deposited corresponding-to-form in an open, two-part form tool 51.1, 51.2 in a press, whereby in the same cycle with a laying device 54 consolidated, plastified continuous fibre strands 3 are laid into the form tool before and/or after the long-fibre-reinforced mass locally defined along predefined laying paths 39 and held in position by means of fixing means 40 to such  
10 an extent, that with the pressing and closing of the form tool 51 a desired supporting structure 4 of the continuous fibre strands 3 is created and whereby with the pressing above all simultaneously also an impeccable thermoplastic connection between the long-fibre mass 2 and the continuous fibre strands 3 is produced at the interface 6.

- In doing so, in preference first the continuous fibre strands 3 are laid in the lower  
15 form tool 51.1 and subsequently the long-fibre-reinforced mass 2 is fed into it, whereupon then the pressing takes place.

- In another variant of the manufacturing method, the continuous fibre strands 3 can be laid on a transport mesh or grid 31 for the formation of a preformed supporting structure 4a, fixed onto it and subsequently transferred to the open form tool 51 (refer  
20 to Fig. 19b). Here the laying of the continuous fibre strands 3 and the feeding-in of the long-fibre mass into the form can take place side by side and simultaneously, as a result of which shorter manufacturing cycles can be achieved. Fig. 13 shows such a transport mesh 31 for laying the continuous fibre strands onto a inlay mesh 32 in a

004707-04E2960

transfer frame 33 for the transfer to the press. The inlay mesh can consist of a coarse meshed textile mesh (e.g., with a mesh width of 4 to 10 mm) and can remain in the structural component after the pressing. The transfer frame 33 is then equipped with a new inlay mesh 32 for the new cycle. By melting the continuous fibre strands into the inlay mesh, a very good fixation corresponding to the required laying path 39 can be obtained.

Utilized as flexible inlay meshes can be, e.g. also fibreglass meshes. By pressing onto the form tool 51, the desired three-dimensional shape of the supporting structure 4a, 4 can be achieved. It is also possible, however, to utilize light, non-deformable metallic wire meshes, with which a three-dimensionally preformed supporting structure 4a can be produced. The transport meshes 31 can also only cover partial areas, in which the laying paths 39 of the continuous fibre strands 3 lie. A further variant consists in the laying of the preformed supporting structure 4a onto a heated auxiliary mould 35 outside the press, as is explained in connection with Fig. 19b.

Fig. 14 shows a structural component with two layers of continuous fibre strands 3.1 and 3.2, which correspond to partial structures 4.1 and 4.2. This can be manufactured by first laying the continuous fibre strands 3.1 in the lower mould half 51.1, subsequently feeding-in the long-fibre mass 2 and carrying out a first pressing. Then the form tool and the press are opened again and a laying path on the long-fibre mass 2 for a second layer of continuous fibre strands 3.2 is superficially melted open by local heating, whereupon a second layer of continuous fibre strands 3.2 is laid, subsequently pressed and in doing so thermoplastically connected with the long-fibre mass 2. This melting open can, e.g., be effected by means of an IR heating to such an extent, that a complete thermoplastic connection is achieved.

Fig. 15, as an example, schematically illustrates the laying of continuous fibre strands along a laying path 39 as a structural component for a vehicle side wall, which here form a framework-like supporting structure 11. The CF strands 3 are here fixed by

means of fixing pins 61, deviating elements 62 and also inserts 21 (here as safety belt anchor points) onto the laying path 39 (also refer to Figs. 6 and 18). In doing so, one or several strands 3, in part also in double or multiple routing can be laid with internal connecting areas 7.

5 The laying and fixation of the continuous fibre strands 3 can, e.g., be carried out in the following manners:

- in that first the beginning 3A of a continuous fibre strand is fixed to the tool 51 and subsequently laid under slight tension, and its end 3E once again, while maintaining an appropriate tension, is fixed to the form tool 51,
- 10 - in that the continuous fibre strand 3 is pressed onto the form by the laying device 54 with such dosing, that the strand lies flat and assumes the desired position and cross-sectional shape in the form tool 51 (Fig. 22),
- in that the continuous fibre strand 3 at least in part, i.e., at the beginning 3A, at direction changes of the laying path and at the end 3E is melted onto the
- 15 mould (41 in Fig. 21),
- in that the continuous fibre strands 3 through contact with the cooler form tool 51 are solidified to such an extent, that they remain fixed to the form tool during the pressing and that they, however, in doing so on the other hand at their contact surfaces 6 again fully fuse together with the long-fibre mass
- 20 2, which has been filled-in in hot condition,
- in that in molten condition at the beginning 3A and end 3E of a continuous fibre strand eyes 43 are melted in by pressing and partial solidifying (Fig. 16) and whereby these shaped ends 3A, 3E after the laying of the continuous fibre strand 3 are superficially melted open again by the hot long-fibre
- 25 molten mass and thermoplastically connected
- and in that at the ends 3A, 3E of the melted-open continuous fibre strands holding elements 45 with plug-in holes 46 are melted open, which after the laying of the long-fibre mass 2 fuse together with it (Fig. 17).

09673340-101400

By an inclined displacement axis 60 during pressing and compression a tensioning effect can also be attained (as shown in the example of Fig. 6a).

Fig. 19a depicts an installation for the manufacturing of structural components with a long-fibre plastifying - and feeding-in device 52, a two-part form tool 51.1, 51.2 in a press 56 and with a continuous fibre strand plastifying device 53, which has an assigned laying device 54, as well as with a control system 57 for the time-coordinated controlling of the movement of the components of the installation and for temperature-conditioning, for laying the continuous fibre strands 3 and for the corresponding-to-form feeding-in of the long-fibre molten mass 2 as well as for the thermoplastic connecting of continuous fibre strands 3 and long-fibre matrix 2.

While in the installation according to Fig. 19a the preformed supporting structure 4a is directly laid and formed by the laying device 54 in the tool 51, Figure 19a as a variant illustrates the formation of the preformed supporting structure 4 outside the press with subsequent transfer into the tool 51 in the press 56 by means of a transfer device 55. To accomplish this, the preformed supporting structure 4a made out of the plastified continuous fibre strands 3 is laid onto an auxiliary mould 35 or onto a suitable substrate, after a slight cooling down to below the melting point, so that an adequate non-deformability is obtained, transferred into the tool 51, there heated up again to such an extent, that with the subsequent filling-in of the hot long-fibre mass 2 and with the pressing a complete thermoplastic connection is produced at the interfaces 6 between the continuous fibre structure 4 and the long-fibre mass 2. Or the preformed supporting structure 4a is laid onto a transport mesh 31 (Fig. 13) and transferred into the press with it. Suitable process temperatures for the materials polypropylene-glass are, for example: for a non-deformable transfer 140° - 150° C, for the hot long-fibre mass 230° - 250° C and for the interfaces 6 during pressing at least 200° C.

Fig. 25 illustrates various examples of fixing - and tensioning elements, with which a preformed supporting structure 4a made out of continuous fibre strands 3.1 to 3.4 is fixed and held within the tool 51 during the pressing, so that following the pressing

the desired finished integrated supporting structure 4 in the long-fibre matrix results. To achieve this, here on the lower form tool 51.1 various fixing elements 61, holding elements 45, deviating elements 62 and tensioning elements 80 are attached. Also clamping elements 81, e.g., made of aluminium sheet metal, which are pressed  
5 together by the pressing, can be utilized for holding the continuous fibre strands together. With this method, in addition simultaneously also, e.g., decorative surfaces 85 (Fig. 19a) can be affixed to one side of the structural component 1 (e.g., for a tailgate 95 in accordance with Fig. 2). On the other side the continuous fibre strands 3, resp., the supporting structure 4 are integrated. By means of such two-side inlays or  
10 supports of a flat surface structural component, the thermal distortion can be essentially reduced.

The Figs. 20 to 22 show further guiding - and fixing means of the installation. In Fig. 20a, b shapings in the form tool 51 are depicted, e.g., like steps 67 in Fig. 20a and channels 66 in Fig. 20b, into which the continuous fibre strands are laid and during  
15 the pressing are held in place, i.e., on the predefined laying path 39.

Fig. 21 illustrates a thermal conditioning on the laying path 39, resp., at the shapings like channels and steps. This can, e.g., consist of a thermal insulating layer 73, which reduces the cooling down of the continuous fibre strand. Also a thermal conditioning 74 can be appropriate, with which the continuous fibre strand 3 depending on the  
20 process step can be heated or cooled. A structuring 75 of the surface, if intended, can also reinforce a local fixation of the CF strands 3 on the form tool 51.

The Figs. 22a to c show guiding - and pressing-on means of the laying device 54. A continuous fibre strand here is guided by guiding rollers 68 on the laying path and by a pressure roller 69 by means of a corresponding control system is deformed and  
25 pressed on to such an extent, that on the one hand the desired cross-sectional shape is

004400-101400

produced and that on the other hand the continuous fibre strand is also pressed onto the form tool 51 and fixed. The laying device 54 can also have two or more pressure rollers (69.2), which can be changed during the laying, in order to by means of this achieve differing shapes, e.g., at connecting areas 7.

- 5 The installation can also be assigned a consolidating device 58 for the continuous fibre strands. The manufacturing of it can be effected, e.g., out of continuous fibre rovings, which are impregnated with matrix material and compacted and consolidated with a suitable torsion. Or else it is also possible to carry out a re-forming of UD (uni-directional) tapes.
- 10 A further variant of the installation comprises a store 59 for the continuous fibre strands, from which the cut-to-length and consolidated strands 3 are taken, completely melted open and laid. In doing so, in preference the continuous fibre strands in the store 59 are preheated to almost their softening temperature.
- 15 If so required, a heating gas - or protective gas conditioning facility 71 can also be foreseen in the installation, in order to on the one hand prevent any oxidizing of the matrix materials and on the other hand to locally dosed heat, resp., cool continuous fibre strands and laying paths 39 in accordance with the process steps.

The Figs. 23 illustrate optimum connections at the interface 6 between continuous fibre strands and long-fibre matrix. Fig. 23a shows an interface 6, which is designed as connecting layer 6a and which can have a layer thickness  $d$  of less than 1 mm, e.g., 0.1 to 0.5 mm. This connecting layer is formed by a mixing - or transition zone, in that the continuous fibre proportion reduces and the long-fibre proportion increases, with which a particularly good thermoplastic connection between continuous fibre



In summary, when laying the continuous fibre strands and in order to form the

supporting structure with internal load-transmitting connecting areas, the following important criteria have to be fulfilled:

- a) The continuous fibre strands have to be laid defined with respect to position on a laying path and
- 5 b) in the desired cross-sectional shape;
- c) they must not be inadmissibly displaced or deformed during pressing, so that in the final condition after the pressing the supporting structure 4 is present in the desired position and cross-sectional shape;
- d) in the final condition they have to be fused together with the long-fibre mass at  
10 the interfaces 6 as well as
- e) with the supporting structures 4 at the internal connecting areas 7 in a load-transmitting manner.

The following means can, for example, be utilized, in order to fulfil these criteria:

- Fix the continuous fibre strands at their beginning 3A and along the laying  
15 path at those points necessary, fix and tension them at deviating means and fixing pins with respect to their shape;
- fix them on the floor of the tool by pressing-on and melting;
- by means of a corresponding shaping of the tool with channels and steps, hold the laid continuous fibre strands firm against displacement;
- 20 - feed-in and distribute the long-fibre masses in such a manner, that during pressing only minimal flow paths of the long-fibre mass occur on the laying paths of the continuous fibre strands;
- feed-in a preformed supporting structure 4a, fix it and with the pressing of the tool form correspondingly bring it to the final shape 4;
- 25 - process control and thermal conditioning of the continuous fibre strands in such a manner, that their surface during pressing fuses together as interface with the long-fibre mass.

With this, in a simple and cost effective manner in short cycles light and stable load-bearing structural components, i.e., light-weight structural components with a to a

004010101000

Within the scope of this description, the following designations are used:

	1	Structural component
	2	Long-fibre matrix
5	3	Continuous fibre strands
	3A	Beginning of 3
	3E	End of 3
	4	Supporting structure
	4.1, 4.2	Partial structures
10	4a	Preformed supporting structure
	6	Interface
	6a	Connecting layer
	6b	Structured interface
	7	Internal connecting areas
15	8	External connecting areas
	9	Thin intermediate layer
	10	Mesh
	11	Framework(-like)
	12	Long-fibre reinforcement (LF)
20	13	Continuous fibres (CF)
	15	CF twisted
	16	CF wrapped
	17	CF braided
	18	Needle-bonded
25	19	Flank, rising
	20	Screw thread
	21	Insert, load-bearing
	22	Inlays
	23	Tubular profile part

	24	Fabric inlay
	25, 26, 27	Three-dimensional (spatial) profile sections
	28	Ribs
	29	Flange
5	31	Transport mesh
	32	Inlay mesh
	33	Transfer frame
	35	Auxiliary mould
	39	Laying paths
10	41	Melt
	43	Eyes on 3
	45	Holding elements
	46	Plug-in holes
	47	Cutting, cutting lines
15	50	Installation
	51	Form tool
	51.1, 51.2	Lower -, upper mould half
	52	LF plastifying and feeding device
	53	CF plastifying device
20	54	Laying device
	55	Transfer device
	56	Press
	57	Control system
	58	CF consolidation device
25	59	CF strand store
	60	Inclined displacement axis
	61	Fixing pins
	62	Deviating elements
	63	Movable
30	64	Controlled drive

	65	Pre-tension
	66	Channels in 51
	67	Steps
	68	Guide rollers
5	69	Pressure rollers
	71	Protective gas / heating gas conditioning
	73	Insulation
	74	Thermal conditioning
	75	Structured surface
10	80	Tensioning elements
	81	Clamping elements
	85	Decorative material
	90	Structural body
	91	Hollow profile girder
15	92	U-profile with ribs
	93	Cover
	95	Tailgate
	96	Floor group
	97	Side walls
20	98	Rear part
	99	Front part
	CF	Continuous fibre
	LF	Long-fibre
	E	Modulus of elasticity
25	d	Thickness of 6a
	d2	Thickness of 2
	d3	Thickness of 3
	F7	Large surface area 7

09673340-103400